

BRONZ-GLOW: RESISTANCE LIST**BRONZ-GLOW® HUSKY
RESISTANCE LIST**

The resistance of Bronz-Glow® Husky to various agents and particles has been tested in lab conditions.

The issue of a warranty to a condenser by the Bronz-Glow® corrosion protection system will be subject to the exposure conditions simulated in this test. Values are based on average concentrations; if there is any doubt, consult the Bronz-Glow® R&D department.

telephone: 01253 890666 fax: 01253 890222

IMPORTANT!!

Resistance is expressed in terms of vapours, not fluids.
Concerning exposure to fluids, cleaning agents, chemicals, process fluids or others, Bronz-Glow® should be consulted.

xx = resistant to concentrated vapours, no limitations to exposure

10-100ppm = resistant until 10-100 ppm

5-10ppm = resistant between 5-10 ppm

-5ppm = resistant until 5 ppm

Temperature 20° C (68° F)

Although the Bronz-Glow resistance list is comprehensive you may operate in an environment not listed in our documentation, if so please contact us and we will assess it to provide the best coating formulation.

telephone: 01253 890666 fax: 01253 890222

BRONZ-GLOW: RESISTANCE LIST

Inorganic acids

• Arsenious acid solution	XX	• Hydrogen sulphide	XX
• Arsenic acid solution	XX	• Hydrogen sulphide solution	XX
• Boric acid	XX	• Nitric acid concentrated	5-10ppm
• Boric acid solution	XX	• Nitric acid solution	XX
• Hydrogen carbonate	XX	• Nitrous acid	XX
• Chromic acid	XX	• Nitrous vapours	5-10ppm
• Bromic acid	5-10ppm	• Sulphuric acid vapours	5-10ppm
• Bromic acid solution	XX	• Sulphuric acid	XX
• Hydrochloric acid	5-10ppm	• Phosphoric acid	XX
• Hydrochloric acid solution	XX	• Perchloric acid concentrated	5-10ppm
• Hydrogen fluoride	XX	• Perchloric acid solution	XX
• Hydrogen fluoride solution	XX	• Selenic acid	XX
• Sulphurous acid	XX	• Selenous acid solution	XX

Organic acids

• Acetic acid	XX	• Oleic acid	XX
• Acetic acid glacial	5-10ppm	• Oxalic acid	XX
• Benzoic acid	XX	• Sulphamic acid	XX
• Lactic acid	XX	• Wine stone acid	XX
• Phenols	XX	• Barn stone acid	XX
• Citric acid	XX	• Palmitic acid	XX
• Fatty acids	XX	• Tannin	XX
• Formic acid concentrated	5-10ppm	• Phthalic acid	XX
• Formic acid solution	XX	• Propionic acid concentrated	5-10ppm
• Hydrocyanic acid	XX	• Propionic acid solution	XX
• Malic acid	XX	• Salicylic acid	XX
• Margoric acid	XX	• Stearic acid	XX
• Picric acid	XX	• Valeric acid	XX

Alkalines

• Ammonia (gas)	10-100ppm	• Caustic potassium	5-10ppm
• Ammonia (Solutions)	10-100ppm	• 7. Potassium hydroxyde solution	XX
• Ammoniacal solution	XX	• 8. Lithium hydroxyde	5-10ppm
• Caustic soda	5-10ppm	• 9. Calciumhydroxyde	XX
• Sodiumhydroxyde solution	XX	• 10. Magnesium hydroxyde	XX

Ethers

• Diethylether	5-10ppm	• Acetic ether	5-10ppm
----------------	---------	----------------	---------

Although the Bronz-Glow resistance list is comprehensive you may operate in an environment not listed in our documentation, if so please contact us and we will assess it to provide the best coating formulation.

BRONZ-GLOW: RESISTANCE LIST**Amines**

• Triethanolamine	XX	• Cyclohexylamine solution	XX
• Triethanolamine concentrated	XX	• Triethylamine	XX
• AMP 95 concentrated	XX	• Aniline	5-10ppm
• AMP 95 solution	XX	• Aniline chloride	5-10ppm
• Aniline sulphate	XX	• Methylamine	XX
• Hexamethylenetetraamine	XX	• Isoferondiamine	XX
• 7. Hexanediamine	5-10ppm	• Diphenylmethanediamine	XX
• 8. Phenylidiamine	XX	• DETHA	XX
• 9. Cyclohexylamine concentrated	5-10ppm		

Aromatic hydrocarbons

• Xylene	XX	• Gumlac	XX
• Toluene	XX	• Benzene	XX
• Asphalt	XX	• Solventnaphta	XX
• Anthracene	XX	• Naphtalene	XX
• Benzapherene	XX	• Terpenes	XX

Aliphatic hydrocarbons

• White spirit	XX	• Isopar G	XX
• White spirit	XX	• Paraffine	XX
• Shellsol TD	XX	• Paraffineoil	XX
• Bitumen	XX		

Alcohols

• Methanol	5-10ppm	• Benzylalcohol	XX
• Ethanol	XX	• Diacetonalcohol DAA	XX
• Isopropanol	XX	• Glycerine	XX
• n-Butanol	XX	• n-Propanol	XX
• Amylalcohol	XX	• Pentanol	XX

Softeners

• Palatinol C	XX	• Desavin	XX
• Chloorparaffine 5XX vl.	XX	• Disflamol TOF	XX
• Dioctylphosphate	XX	• Mesamol	XX
• Dibutylphosphate	XX	• Dinonylphenol	XX

Although the Bronz-Glow resistance list is comprehensive you may operate in an environment not listed in our documentation, if so please contact us and we will assess it to provide the best coating formulation.

BRONZ-GLOW: RESISTANCE LIST

Fuels & Oils

• Diesel	XX	• Mineral Oils	XX
• Fuel oil	XX	• Breakliquide	XX
• Petrol	XX	• Skydrol	XX
• Superpetrol	XX	• Aninal oils	XX
• Lubricating oils	XX	• Ethric oils	XX
• Kerosene	XX	• Vegetable oils	XX
• Sferic oils	XX	• Butagas	XX
• LPG	XX	• Acetylene	XX

Esters

• Ethylacetate	10-100ppm	• Butylacetate	XX
• Amylacetate	XX	• Butylpropionate	XX
• Propylacetate	XX	• Ethylformiate	XX
• Ethyloxalate	XX	• Ethylbenzoate	XX

Ketones and Aldehydes

• Acetone	10-100ppm	• Crotonaldehyde	5-10ppm
• Aceetaldehyde	5-10ppm	• Formaldehyde	5-10ppm
• Benzaldehyde	10-100ppm	• Salicylaldehyde	5-10ppm
• Diisobutylketone	5-10ppm		
• Methylisobutylketone	5-10ppm		
• Methylethylketone	5-10ppm		
• Butanal	5-10ppm		

Halogenated Hydrocarbons

• 1.1.1.Trichloorethane	5-10ppm	• Trichloorethylene	5-10ppm
• Methyleenchloride	5-10ppm	• Perchloorethylene	5-10ppm
• Methylbromide	5-10ppm	• Tetraiodicmethane	5-10ppm
• Tetrachloormethane	5-10ppm	• PCB	5-10ppm
• Dichloorethene	5-10ppm		

Although the Bronz-Glow resistance list is comprehensive you may operate in an environment not listed in our documentation, if so please contact us and we will assess it to provide the best coating formulation.

BRONZ-GLOW: RESISTANCE LIST

Salts & Water solutions

• Sodiumsalts	XX	• Hydroquinone	XX
• Potassiumsalts	XX	• Ironsalts	XX
• Calciumsalts	XX	• Processwater	XX
• Aluminiumsalts	XX	• Rainwater	XX
• Ammoniumsalts	XX	• Seawater	XX
• Bariumsalts	XX	• Heavywater	XX
• Coppersalts	XX	• Zincsalts	XX
• Leadsalts	XX	• Tinsalts	XX
• Lithiumsalts	XX	• Siliconsalts	XX
• Magnesiumsalts	XX	• Cement	XX
• Mercurysalts	XX	• Quarts	XX
• Lithopone	XX	• Dolomite	XX
• Arsenious compounds	XX		

Others

• Carbondisulphide	10-100ppm	• Camphor	XX
• Carbonmonoxyde	XX	• Carbon	XX
• Carbondioxyde	XX	• Cellulose	XX
• Nitrogen	XX	• Celluloseacetate	XX
• Hydrogenperoxyde	10-100ppm	• Nitrocellulose	XX
• Chlorine	5-10ppm	• Methylcellulose	XX
• Chlorine water	5-10ppm	• Cocos	XX
• Iodine	5-10ppm	• Silicium	XX
• Iodinetinctuur	10-100ppm	• Siliciumcarbide	XX
• Bromic	5-10ppm	• Cork	XX
• East-Indian ink	XX	• Woodfibre	XX
• Phosphor	XX	• Photo-developmentbathe	XX
• Diphosphorpentoxyde	5-10ppm	• Viscose	XX
• Zinc	XX	• Rescosinol	XX
• Aluminium	XX	• Resins	XX
• Glucose (syrup)	XX	• Tabaco	XX
• Fructose	XX	• Nicotine	XX
• Mercury	XX	• Trinitrobenzene	XX
• Sulpher	XX	• Gelatine	XX
• Antimony	XX	• Printer's ink	XX
• Indole	XX	• Milk	XX
• Latices	XX	• Potatoflour	XX
• Nitroglycerine	XX	• Vegetables	XX
• Hydrogen	XX	• Fruit	XX
• Epoxyresins	XX	• Spices	XX
• Isocyanate	XX	• Honey	XX
• Rubber	XX	• Eggs	XX
• Schellac	XX	• Cheese	XX
• Soaps	XX	• Mustard	XX
• Urea	XX	• Mayonnaise	XX
• Thiourem	XX	• Tomato Ketchup	XX
• Fruit essences	XX	• Curry	XX
• Beer	XX	• Cacao	XX
• Flourproducts	XX	• Lemonade	XX
• Corn	XX	• Coca Cola	XX
• Liqueurs	XX	• Pepsi Cola	XX
• Coffee	XX	• Sauerkraut	XX
• Tea	XX	• Blood	XX
• Liqueur	XX	• Ketjap	XX
• Menthol	XX	• Sambal	XX

Although the Bronz-Glow resistance list is comprehensive you may operate in an environment not listed in our documentation, if so please contact us and we will assess it to provide the best coating formulation.